

FIBRANgeo B-001

Semi Rigid Stonewool insulation board









Product Description

FIBRANgeo B-001 Semi Rigid Stonewool insulation board is semi rigid, industrially produced from molten rock spun into fibres.

It is classified as mineral wool product for use in building insulation, according to the European Standard EN 13162 (MW - Mineral Wool insulation products).

Stonewool is a natural inorganic fibrous material, widely recognised for its thermal and sound insulating properties, as well as its excellent performance towards fire protection.

FIBRANgeo B-001 is produced from mineral rock, initially fused in an electric furnace at 1520°C and then spun into fibres. The loose stonewool fibres, with the addition of adhesive resin, oil and special silicon compounds that provide hydrophobicity, become cohesive, elastic, non-hygroscopic and water-repellent, formed in boards and finally shrink-wrapped in PE film in packages. The non-use of fossil fuels (e.g. coke) as a main production fuel minimises polluting gas emissions in the environment.

Advantages

- Excellent thermal insulation
- Excellent sound absorption and sound reduction
- Non-combustible material with excellent fire resistance
- Open hive structure material with very low water vapour diffusion resistance, similar to the resistance of air (μ =1), enhances the building elements' breathability
- Water repellent and non-hygroscopic
- Natural, inorganic, odourless, chemically inert (practically neutral PH)
- Lightweight, easy to handle, cut and install
- Resistant to vibrations
- Does not allow the development of micro-organisms, insects or rodents
- Recyclable
- Friendly to the environment and to the end user



Applications

FIBRANgeo B-001 is suitable for use in all building types and constructions.

- A) Thermal-acoustic-fire insulation of cavity in vertical building elements, such as:
 - Twin-skin metal wall cladding (on site construction) with core insulation
 - Masonry cavity walls
 - Insulation of ventilated facade (e.g. dry board cladding, marble, ceramic tile, metal panels)
 - Dry construction walls with core insulation (gypsum boards, timber panels, etc.)
 - Masonry walls with dry lining / cladding (gypsum boards, cement boards, metal panels, etc.)
 - Walls with perforated dry lining (gypsum panels, metal panels, etc.)
- B) Thermal-acoustic-fire insulation of cavity in horizontal building elements, such as:
 - Between roof frame elements (rafters, beams, joists)
 - On attic ceiling lining
 - Between timber floor joists
 - Pilotis external insulation with dry board cladding
 - Dry construction ceiling (gypsum board, etc.)
 - On non-perforated suspended ceiling lining
 - On perforated ceiling lining
- C) Construction of:
 - Acoustic-thermal-fire insulating panels
 - Acoustic-thermal-fire insulating doors

Packaging

Thickness [mm]	Width [mm]	Length [mm]	Boards/ package [pc]	Quantity/ package [m²]	Packages/ pallet [pc]	Quantity/ pallet [m²]
20	600	1200	15	10,80	16	172,80
30	600	1200	10	7,20	16	115,20
40	600	1200	8	5,76	14	80,64
50	600	1200	6	4,32	16	69,12
60	600	1200	5	3,60	16	57,60
70	600	1200	5	3,60	14	50,40
80	600	1200	4	2,88	14	40,32
100	600	1200	3	2,16	16	34,56
120	600	1200	2	1,44	20	28,80
140	600	1200	2	1,44	18	25,92
160	600	1200	2	1,44	14	20,16



Other dimensions are available upon request.

Facings

FIBRAN*geo* **B-001** is available with the following standard facings to meet particular application requirements:

- FIBRANgeo B-001-AL Aluminum foil reinforced with fibreglass net
- FIBRANgeo B-001-AX Aluminum kraft paper foil reinforced with fibreglass net
- FIBRANgeo B-001-YM Black non-woven fiberglass fleece
- FIBRANgeo B-001-YA White non-woven fiberglass fleece
- FIBRANgeo **B-001-XA** Kraft paper





Designation code:

MW(Mineral Wool) - EN 13162 - T4 - CS(10)10 - WS - WL(P) - MU1 - SD5 - AW1 - AF60

Technical Characteristics	Symbol EN-13162	Unit	Value	EN standard	
Declared thermal conductivity at 10 0 C	λ_{D}	W/(mK)	0,033	EN 13162 EN 12667 EN 12939	
Nominal thickness	d_N	mm	20 - 160	EN 823	
Fire classification	-	Class	A1 (Non-combustible)	EN 13501-1	
Melting temperature		°C	>1000	DIN 4102-17	
Specific heat capacity	c	kJ/kg*K	0,84	-	
Thickness tolerance	Т	Class	T4 (-3, +5 mm)	EN 13162	
Compressive Stress at 10% thickness deformation	CS(10)	kPa	5 (d _N ≤60) 10 (d _N >60)	EN 826	
Dynamic Stiffness, s' (Board Thickness 80 mm)	SD	MN/m³	5	EN 29052-1	
Short Term Water Absorption for 24 h	WS	kg/m ²	<1	EN 1609	
Long Term Water Absorption for 28 days	WL(P)	kg/m ² <3		EN 12087	
Water vapour diffusion resistance factor μ	MU	- 1		EN 12086	
Air flow resistivity, r	AF_r	kPa s/m²	60	EN 29053	
Weighted Sound Absorption Coefficient α_w (Board Thickness 50 mm)	AW	-	1 (Class A)	EN ISO 11654 EN ISO 354	
Density, ρ	-	kg/m ³	100	EN 1602	

Thermal resistance R


Nominal thickness	d_N	mm	20	30	40	50	60	70	80	100	120	140	160	EN 823
Thermal resistance	R_{D}	m ² K/W	0,60	0,90	1,20	1,50	1,80	2,10	2,40	3,00	3,60	4,20	4,80	EN 13162



Sound Absorption Coefficient α_s (EN ISO 354)

(Board Thickness 50 mm)

Test Report: I.G. / 168182



Frequency (Hz)	$\alpha_{ m s}$	$\alpha_{ extbf{P}}$	$lpha_{ m w}$		
125	0,14	0,20			
250	0,79	0,75	0,80		
500	1,05	1,00	1,00		
1000	1,10	1,00	1,00		
2000	1,01	1,00	1,00		
4000	0,87	0,90	0,90		

Weighted Sound Absorption Coefficient α_w = 1 - Class A (EN ISO 11654) Noise Reduction Coefficient NRC = 1 (ASTM 423)









Certifications

All FIBRANgeo stonewool insulation products meet the QUALITY and SAFETY requirements of the European Standards.

The quality of FIBRANgeo products is assured in accordance with EN 13162 and EN 13172 standards. These standards establish the type and frequency of measurements executed both by recognised and independent institutions, as well as by FIBRAN laboratories.

CE Certification

All FIBRAN*geo* stonewool insulation products conform to the European Directive 89/106/EEC since 2004. In compliance with the above Construction Products Directive, all types of FIBRAN*geo* stonewool products hold the CE marking. Further, they are in conformity with the European Norm EN 13162, which refers to mineral wool insulation products used in building applications.

- Notified Bodies: Forschungsinstitut für Wärmeschutz e.V. München (FIW): Identification Number 0751
- Materialprüfanstalt für das Bauwesen Hannover (MPA BAU): Identification Number 0764

EUCEB Certification

All FIBRAN*geo* stonewool insulation products also carry the certification mark EUCEB (European Certification Board for Mineral Wool Products). EUCEB is an independent organization whose procedures ensure compliance of mineral wool insulation products with the Directive's 97/69/EC, Note Q, regarding their fibres biosolubility and their non-classification as 'carcinogenic' materials.

Moreover, according to EC Regulation 790/2009 (August 10, 2009) they are not classified as products that cause skin irritation.

ISO 9001:2008 Certification

The quality management system of FIBRAN S.A. complies with EN ISO 9001:2008 for the design and manufacture of Mineral Wool (MW), as certified by the independent body TÜV NORD CERT, with initial Certificate Registration No. 04 100 960680.



Handling and Storage

FIBRAN*geo* products should be stored indoors. If stored outdoors, they must be protected from impregnation. Pallets shrink-wrapped weather tightly in PE film may be stored outside. Separate packages should be placed on a flat pallet, not in direct contact with the ground.

If part of the product gets wet, it must be dried before installation. Stonewool dries quickly and its insulating properties remain unchanged after drying.

FIBRANgeo products are chemically inert and do not allow the growth of micro-organisms, insects or rodents.

Handling, loading and unloading of the products should be carried out with care, to avoid damage both the packaging and the boards' edges.



For the selection and application of FIBRANgeo products all design requirements should be taken into consideration.

FIBRANgeo products should be protected from impregnation, prior to and during application.

The packaging film should be removed with care just before installation.

Working areas should be kept clean. Unnecessary or extensive contact of the skin and eyes with products off-cuts, fibres and dust should be avoided, and protective wear should be used (gloves, goggles, hats).

Sufficient ventilation of the working areas should be ensured, whilst power cutting tools should always be provided with a mechanical system of dust intake.

Stonewool products are not considered hazardous waste. Waste disposal should be carried out according to State and Local regulations.













THESSALONIKI FIBRAN S.A. 6th km Thessaloniki-Oreokastro Rd. P.O. Box 40306, A.C. 560 10 Thessaloniki, Greece Tel. +30 2310 682 425, 692 700 Fax. +30 2310 683 131 ATHENS IZO-TEC S.A., 37 Ag. Athanasiou str., A.C. 145 69, Anoixi Attikis, Greece Tel. +30 210 8141 414, 8142 415 Fax. +30 210 8141 850



info@fibran.gr www.fibran.gr

FIBRAN reserves the right to alter or amend product specifications without notice. The information included in this publication is correct to the best of our knowledge at the time of printing. Whilst FIBRAN will endeavour to ensure publications are up to date, it is the user's responsibility to check with the company the validity of the information prior to materials' use.

TECHNICAL DATA SHEET